

**PRODUCT INFORMATION**

Norm	EN ISO 26986			
Intensity of use	ISO 10874 (EN 685)		23 domestic heavy 32 commercial general 41 industrial moderate	class
Total thickness	EN ISO 24346 (EN 428)		2,90	mm
Wear layer	EN ISO 24340 (EN 429)		0,40	mm
Total weight	EN ISO 23997 (EN 430)		1950	g/m <sup>2</sup>
Standard width	EN ISO 24341 (EN 426)		2 - 3 - 4*	m
Standard length	EN ISO 24341 (EN 426)		+/- 28	m

**TECHNICAL INFORMATION**

Abrasion group	EN 660-2		T	class
Dimensional stability	EN ISO 23999 (EN 434)		≤ 0,40	%
Curling	EN ISO 23999		≤ 8	mm
Light stability	EN ISO 105 B02		≥ 6	degree
Residual indentation	EN ISO 24343-1 (EN 433)		≤ 0,20	mm
Impact sound improvement	EN ISO 717/2		Δ Lw 16	dB
Dynamic coefficient of friction	EN 13893		> 0,60	
Slip resistance (ramp test with oil)	DIN 51130		R10	scale
Reaction to fire	EN 13501-1		Bfl-s1	class
Underfloor heating	EN 12667		suitable	
Thermal resistance	ISO 8302		0,025	m <sup>2</sup> .K/W
Thermal conductivity	EN 12524		0,12	W/(m.K)
Chemical resistance	ISO 26987 (EN 423)		resistant	
Static electrical propensity	EN 1815		< 2kV	on concrete
Castor chair resistance	EN ISO 4918		suitable (type wheel W)	
Cold welding	Werner Müller		type A	

\* check individual ref. for available widths

Please note that the data given could be imprecise and liable to modifications of a technical nature at any time. The information in these documents is valid from 17/03/2025 and Beauflor reserves the right to make changes at any moment and without prior notice. Our technology is constantly evolving, so before carrying out any projects we encourage you to contact us to maintain our highest level of standards.

**SUSTAINABILITY**

We feel that it's our moral duty to contribute to a more sustainable world. This is illustrative by the choice of raw materials, of partners, of transport and of fabrication processes. Our selection of core materials is based on a combination of our clients' requirements for a quality product as well as requirements for a minimal impact on the environment.

Ortho-phthalates free

- No heavy metals
- No solvents
- No formaldehyde
- No harmful plasticizers

**E1**  
Approved for  
EN15303v2

Level of formaldehyde is inferior to 0.1ppm (= 0.12 mg/m<sup>3</sup> of air)

**MISSIONS DANS L'AIR INTÉRIEUR**

**A+**

Our products are classified as A+ for the emission of volatile substances in inside air (compulsive sanitary labelling in France since January 2012)

**floor score**

certified by

**BB**

Approbation zur gesundheitlichen Bewertung von Bauprodukten

**FEATURES**

EN 14041

**CE**

**05**

**DOP: 450-TC0013-1**

B.L.G. - Flooroverlays NV  
Rijsweg 442, 9710 Wierdenbeke  
BELGIUM  
NB: 0534  
Resilient floor covering for use within buildings